



# BODY 960 WASH PRIMER

Technical Data Sheet No 111

VOC compliant with the regulations

Suitable for Galvanised Stainless Steel Aluminium

Excellent metal protection

Easy to apply

Excellent physical protection

## General Technical Description



Mix 100 parts BODY 960 WASH PRIMER with 100 parts BODY ACTIVATOR

Air dry 30min / 23°C (73°F)

## Surface

Aluminium Surfaces

Stainless Steel

Galvanised Surfaces

Zinc Surfaces

## Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST.

Make sure the surface is first wiped dry and then air dried



Make sure you always use appropriate face protection and good ventilation

## Product Application: A 2K Acid Curing Primer

1 pass »» Apply a thin layer over sanded areas only



1:1 mix with BODY 960 ACTIVATOR  
Pot life: >6hrs @ 23°C (73°F)



Non force dry  
30min / 23°C (73°F)



No Thinner Addition



Always wear protective equipment



Ready to spray:  
20 s  
DIN 4 @ 20°C (68°F)



Follow the application instructions mentioned in this TDS



Compliant Spray gun  
1.4mm  
2-3 bar (29-44psi)  
inlet pressure  
1x coat = 5-10 µm  
(0.2-0.4mil)



- 2K HB BODY Primers
- HB BODY Color Solutions Basecoat
- HB BODY Color Solutions 2K
- HB BODY Clears



HVLP Spray gun  
1.4mm  
2 bar (29psi)  
inlet pressure  
1x coat = 5-10 µm  
(0.2-0.4mil)

**\*\* Warning :** Do not use on top of BODY 960 WASH PRIMER monodrying polyesters (i.e polyester putties)



30 min / 23°C (73°F)  
Final flash off time

**Flash Point:**  
13°C / 55°F

**Specific Gravity:**  
0.95 g/cm<sup>3</sup>

**Solid Content (No thinner):**  
29% Weight

**VOC (2004/42/EC)**  
This is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 780 g/L. The VOC content in the ready for use form of this product is 720 g/L.  
2004/42/II(c)(780)720

**Theoretical Coverage:**  
7-8 m<sup>2</sup> / l at 10micron (0.4mil) dry film thickness

**Cleaning of equipment:**  
Clean after final use with Body 740 ACRYL NORMAL

## Remarks:

- Allow for additional time for combi spray booths to reach the desired temperature
- Application only with the recommended hardeners and solvents
- It can be used by countries that do not adopt the VOC legislation.
- Do not use at temperatures below 15°C (59°F).

## Storage Shelf life:

- Store in a cool place (+5°C to 25°C) (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 6 / 2018, January 2018